

ZHEJIANG ZHONGJIE PACKAGING MATERIAL CO.,LTD

ADDRESS: No 145,Liminghu road,YiWu City,ZheJiang Province,China

TELL: +86 579 85417939

Website: www.zhongjiepack.com

Certificate of Analysis

Type 品名	PET Holographic film	Date 日期	2023-6-27
No. 编号		Operator 检测人员	HZHANG
Condition 测试条件	Temperature23℃ Humidity50%	Film Class 薄膜等级	A GRADE
Remark 备注	PRINTING AND PACKAGING		
Properties 检测项目	Units 单位	Typical Values 测试参考值	Test Methods 测试方法
Tensile Strength 纵向 MD 拉伸强度 横向 TD	micron MPa MPa	16 219 248	DIN 53370 ASTMD882
Opitical Density(光学密度)	-	2.1	TSI Method
Elongation 纵向 MD 断裂伸长率 横向 TD	% %	138 110	ASTMD882
Heat Shrinkage 加热收缩率 纵向 MD (150℃、30min) 横向 TD	% %	1.60 -0.04	BMSTT11
Wetting Tension (Treatment Side) 润湿张力(处理面) 横向 TD	mN/m	44	ASTM2578
Haze 雾 度 横向 TD	%	1.95	ASTM1003
Corona	Dyne	46	ASTM2588
Density(密度)	-	1.4	

备注: 1. The above values can not be understood as guarantee value or contract item.
They can only be used as test reference.